



STLSM
STANDARDS
TESTING LABS

Tough On Testing.SM

St. Barsabas Inc.

L1-803

TEST NO. STB1-1199

DATE 4/15/02

MATERIAL RUBBER

STATION NO. 22

PART NO. RUBBER-STEEL RIM

	DATE	START TIME	END TIME	TECH	TEST LOAD (LBS)	ACTUAL LOAD (LBS)	SPEED (MPH)	AMBIENT (°F)	INFRARED (°F)	COAST TIME (sec)	RUN OUT (RADIAL)	RUN OUT (LATERAL)	COMMENTS
S.	4/15/02	1045	1046	ES	400	400	15	98					15 Sec. Warm-up
0.					400		0						Failure during warm-up.
1.					400		70						Rubber melted around
2.					400		70						wheel flange.
3.					400		70						
4.					400		70						
5.					400		70						
6.					400		70						
7.					400		70						
8.					400		70						
9.					400		70						
10.					400		70						
11.					400		70						
12.					400		70						
13.					400		70						
14.					400		70						
15.					400		70						
16.					400		70						
17.					400		70						
18.					400		70						
19.					400		70						
20.					400		70						
21.					400		70						
22.					400		70						
23.					400		70						
24.					400		70						
25.					400		70						

TECHNICIAN : E. Stephens

DATE COMPLETED: 4/15/02